

# 雅化 200 (1/4)



准备工序助剂 | 去污垢

## 成份

雅化 200 是一种有机化工，用于浸灰不会产生有毒的胺。

雅化 200 在正常去肉皮，可以减少粒面皱纹。

用于脱毛裸皮（为辅助剂），赋予很平坦而清洁的裸皮。（与很少皮面的黑色皮垢.皮垢能产生裂面.）

雅化 200 去皮垢，优良天然动物油脂及污泥分散性。

雅化 200 帮助打开纤维，使皮革具有柔软，紧实而结实皮。

## 应用范围

A. 用于浸灰浴（1.5% 盐皮重量）

## 特性

外观:	水状清澈至浅绿液体
分析:	pH 3.0-6.0
有效成份:	45-48%
密度:	1.10-1.20 KG/L
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

## 包装

120KGS 塑料桶  
200KGS 铁桶

继续下页

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 雅化 200 (2/4)

准备工序助剂 | 去污垢



## 划槽浸灰

	已去肉盐皮		
250%	水 (25C)		
1.5%	<b>雅化 200</b>	60'	
	正常加硫化氢钠，硫化钠及石灰。		

## 转鼓浸灰

	已去肉盐皮		
150%	水 (20-22C)		
1.5%	<b>雅化 200</b>	120'	
	正常加硫化氢钠，硫化钠及石灰。		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 雅化 200 (3/4)



准备工序助剂 | 去污垢

盐皮到蓝湿皮   牛盐皮   盐皮重量				
厚度				
预浸水	200%	水 25-27°C		
	0.2%	雅化 DDA	90'	
				排水
洗水		水 25-27°C	10'	
				排水
主浸水	200%	水 25-27°C		排水
	0.3%	雅化 DDA		
	0.3%	小苏打	5'/60' for 360'	
				排水
洗		水 25-27°C	20'	
				排水
去肉				
浸灰	200%	水 25-27°C		
	3.0%	亚硫酸钠	30'	
	3.0%	石灰		
	0.3%	雅化 DDA	5'/60' 自动过夜	
				排水
洗水	200%	水 25-27°C	10'	
				排水
去肉				
洗水	200%	水 25-27°C		
	0.2%	雅化 ANF	20'	
				排水
去肉, 片皮 % 片皮重量				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 雅化 200 (4/4)

准备工序助剂 | 去污垢



盐皮到蓝湿皮   牛盐皮   片皮重量				
洗水	20%	水 25-27°C		
				排水
洗水	200%	水 25-30°C		
	0.2%	雅化 DDA	20'	排水
脱灰	200%	水 25-30°C		
软化	2.5%	硫酸铵		
	0.5%	亚硫酸氢钠		
	0.1%	雅化 DDA	45'	pH=8.4-8.6
				检查 Ø
	0.5%	Oropon OO 浸酸酶	20'	
				排水
浸酸浴	40%	水 25-30°C		
	5.0%	盐		
	2.0%	依丽卡隆 50MD	20'	
				检查 Be > 6
	0.9%	甲酸 85% (1:10)	20'	
	0.9%	硫酸 96%	120'	pH=2.5-2.6
	3.0%	铬粉	30'	
	4.0%	铬粉		
	0.25%	氧化镁	180'	自动过夜
		次日, 检查 pH 值		
	1.0%	小苏打	10' X 4 + 30'	
				pH=3.7-3.8
		检查煮沸试验		
				排水
		搭马过夜, 挤水, 削匀 1.0 mm.		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".