

# 雅丽芬 BLACK 999 2AM (200%) (1/4)



喷涂黑颜料膏 | 无酪素

## 成份

雅丽芬 Black 999 2AM (200%) 由纳米碳黑微粒组成，优良分散性和稳定性，有特优的遮盖力和黑度且不会增加粒面负荷。

## 应用范围

- A. 软全粒面鞋面革
- B. 修面革
- C. 二层革
- D. 家俱革
- E. 可在涂饰液中加入黛丽丹黑 Black AS 来调整黑度
- F. 为避免加入过快反应,建议先将树脂搅拌加入,再将雅丽芬 Black 999 2AM (200%) 及酪素等混合加入雅丽芬 Black 999 2AM (200%)是高浓度颜料膏, 仅需普通颜料膏的一半

## 特性

外观:	黑色液体
分析:	pH 8.7-9.7
有效成份:	27-29%
密度:	1.10-1.20 KG/L
储存方法:	室温。对霜冻敏感。 建议使用前进行充分搅拌。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

## 包装

35KGS / 120KGS 塑料桶

继续下页

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 雅丽芬 BLACK 999 2AM (200%) (2/4)



喷涂黑颜料膏 | 无酪素

## 应用配方

	350-400	树脂		
	X	填料		
	X	蜡		
	X	酪素		
	X	水		以上化工材料混合
	50	雅丽芬 Black 999 2AM (200%) 黑膏		
	X	水		

## 应用配方 (1)

1	50	雅丽芬 Black 999 2AM (200%) 黑膏		
2	50	填料 MP 消光填料		
3	100	蜡 H 蜡		
4	50	树脂 S 丙烯酸树脂		
5	150	树脂 S 205 丙烯酸树脂		
6	150	树脂 EB 综合树脂		1+2+3+4+5+6
7	600	Water 水		
8	70	PL-1 渗透剂		7+8
刷浆两次，弄干。真空，摔软 2 小时。				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 雅丽芬 BLACK 999 2AM (200%) (3/4)



喷涂黑颜料膏 | 无酪素

## 应用配方 (2)

1	50	雅丽芬 Black 999 2AM (200%) 黑膏		
2	50	填料 MP 消光填料		
3	100	蜡 H 蜡		
4	100	树脂 S 丙烯酸树脂		
5	150	树脂 EB 综合树脂		
6	150	树脂 S 205 丙烯酸树脂		1+2+3+4+5+6
7	600	Water 水		
8	70	渗透剂 PL-1		7+8
刷浆两次，弄干。真空，摔软 2 小时。				

## 应用配方 (3)

1	50	雅丽芬 Black 999 2AM (200%) 黑膏		
2	50	填料 MP 消光填料		
3	100	蜡 H 蜡		
4	100	树脂 S 丙烯酸树脂		
5	150	树脂 S-100 复合树脂		
6	150	树脂 S 205 丙烯酸树脂		1+2+3+4+5+6
7	600	Water 水		
8	70	渗透剂 PL-1		7+8
刷浆两次，弄干。真空，摔软 2 小时。				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 雅丽芬 BLACK 999 2AM (200%) (4/4)



喷涂黑颜料膏 | 无酪素

## 应用配方 (4) 遮盖黑色纳帕软鞋面

1	50	雅丽芬 Black 999 2AM (200%) 黑膏		
2	50	填料 MP 消光填料		
3	100	蜡 H 蜡		
4	100	树脂 S 丙烯酸树脂		
5	150	树脂 783MC 聚合物树脂		
6	150	树脂 S 205 丙烯酸树脂		1+2+3+4+5+6
7	600	Water 水		
8	70	渗透剂 PL-1		7+8
刷浆 1 次, 弄干。真空 60 度 60 秒。弄干。				
刷浆 2 次, 弄干。真空 60 度 60 秒。弄干。				
9	250	Lacquer Black 黑光油		
10	250	Lacquer Clear 透明光油		
11	15	Feel Improver 手感剂		
12	500	Water 水		
喷涂 1 次。真空 90 度 30 秒。做软 5 号。摔软 8 小时。				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".