

ALTAN MC

鞣助剂 | 铬铈链剂



成份

Altan MC 由配位盐, 是一种多用途材料.

在铬鞣浴中, **Altan MC** 对腹部及其他松弛部分加以填充, 使皮软度及饱满均匀.
在铬鞣浴中, **Altan MC** 降低废水铬金属分量, 提升铬固定性.

Altan MC 帮助蓝湿皮染料渗透性.

Altan MC 提升植鞣革丰满度.

Altan MC 将加强白皮的白度, 浅色的亮度, 并同时不影响暗色.

会将加强对白色皮革白度和亮度将浅色, 并在同一时间将不漂白暗色.

应用范围

- A. 各种皮革: 浸酸浴: 盐后加入 1.3-1.5% 裸皮重量, 转 30 分钟
- B. 各种蓝皮: 铬复鞣浴: 2-3% 蓝湿皮重量, 转 30 分钟. 再加铬粉 X% 铬粉
- C. 各种蓝皮鞋面革: 染色浴: 染料加入前 2-4% 蓝湿皮重量, 转 30 分钟.
- D. 植鞣革: 复鞣浴: 2-4% 削匀重量.

特性

外观:	清澈液体
分析:	pH 11.0-13.50
有效成份:	37-39%
密度:	1.25-1.30 KG/L
稳定性:	浸酸, 铬复鞣, 复鞣浴
储存方法:	室温. 如出现霜冻, 搅拌均匀即可. 存放在阴凉及通风的库房.
保质期:	密封容器约 18 月.

包装

150KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".