

ALTAN MS

鞣助剂 | 铬铈链剂



成份

Altan MS 由有机盐组成, 在铬鞣液中和铬粉组成混合物.

Altan MS 在鞣液中, 对腹部及其他松弛部分加以填充.

由于有很好的结合能力, **Altan MS** 可使大部分铬粉在水浴中被吸收, 废液中铬粉含量很低.

在铬鞣浴中, **Altan MS** 降低废水铬金属分量, 提升铬固定性.

Altan MS 帮助蓝湿皮染料渗透性.

Altan MS 提升植鞣革丰满度.

应用范围

- A. 盐后加到浸酸液中 (以裸皮重的 1.3-1.5% 计算)
- B. 用于铬复鞣浴中帮助铬朗好吸收 (以蓝湿皮重量的 2-4% 计算)
- C. 各种蓝皮鞋面革: 染色浴: 染料加入前 2-4% 蓝湿皮重量, 转 30 分钟.
- D. 植鞣革: 复鞣浴: 2-4% 削匀重量.

特性

外观:	浅粉红清澈透明液体
分析:	pH 11.0-13.5
有效成份:	37-39%
密度:	1.25-1.30 KG/L
稳定性:	浸酸, 铬复鞣及复鞣浴
储存方法:	室温. 如出现霜冻, 搅拌均匀即可. 存放在阴凉及通风的库房.
保质期:	密封容器约 18 月.

包装

150KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".