

依丽卡隆 50MD (1/3)



海类型动物亚硫酸化加脂剂

成份

依丽卡隆 50MD 是一种特稳定的小分子亚硫酸化海类型动物油为主加脂剂。

依丽卡隆 50MD 用在浸酸浴中能帮助打开皮面的皱纹，使皮革具有非常软，蓬松舒适及平滑的手感。

依丽卡隆 50MD 已经完全脱臭海洋油气味，并会产生异常精细乳液。

使用在回水浴中，依丽卡隆 50MD 可提高撕裂度。

依丽卡隆 50MD 冷天不会产生任何油霜，即使长时间储存不会产生任何异味。

依丽卡隆 50MD 可以和其它油脂混合改善油脂的稳定性。

为了达到最好的效果 依丽卡隆 50MD 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 各种皮革：浸酸浴：至 2.5% 依丽卡隆 50MD 裸皮重量。

B. 各种蓝湿皮：铬复鞣浴：2-3% 依丽卡隆 50MD 消匀重量。

C. 各种蓝湿皮：回水浴：至 2% 依丽卡隆 50MD。

特性

外观:	棕色液体
分析:	pH 4.5-6.0
有效成份:	66-69%
电性:	阴离子
稳定性:	用于浸酸，铬复鞣，复鞣浴。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

依丽卡隆 50MD (2/3)



海类型动物亚硫酸化加脂剂

直接沙发革 | 牛蓝湿皮 | 削匀革重

厚度				
洗水	400%	水 25-30°C		
	0.7%	雅化 325W		
	1.0%	雅化 CSAM	30'	pH=3.2-3.5
				排水
	中和	200%	水 25-30°C	
	2.0%	依丽卡隆 6SKT		
	2.0%	甲酸钠	30'	
	0.8%	小苏打	60'	pH=5.8-5.9
				排水
	复鞣	150%	水 25-30°C	
	5.0%	替代型单宁	15'	
	15.0%	单宁		
	5.0%	替代型单宁	90'	
	0.8%	甲酸 85% (1:10)	15'	pH=4.0
				排水
洗水	300%	水 25-30°C	10'	
				排水
染料	50%	水 25-30°C		
	0.5%	氨水 25% (1:10)	10'	
	1.0%	分散单宁		
	2.0%	分散单宁		
	2.5%	染料	60'	检查 Ø
	150%	水 45-50°C		
	10.0%	优卡隆 N7YC		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

依丽卡隆 50MD (3/3)

海类型动物亚硫酸化加脂剂



直接沙发革 | 牛蓝湿皮 | 削匀重量

	4.0%	依丽卡隆 50MD	90'	
	0.75%	甲酸 85% (1:10)	15'	
	0.75%	甲酸 85% (1:10)	30'	pH=3.3
				排水
洗水	200%	水 25-30°C	10'	
				排水
搭马过夜, 伸展, 湿绷板, 喷水回湿, 做软, 摔软, 绷板, 烫.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".