

依丽卡隆 6SKT (1/3)



亚硫酸化加脂剂

成份

依丽卡隆 6SKT 是一种复合加脂剂，由亚硫酸化海类型动物油乳化剂，硅油及溶剂组成。

依丽卡隆 6SKT 是专为平衡内心柔软性能，同时没有牺牲任何性能。

为了达到最好的效果 依丽卡隆 6SKT 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 家俱革：6-8% 依丽卡隆 6SKT.

B. 纳帕鞋面革：3-4% 依丽卡隆 6SKT.

C. 箱包革：4-6% 依丽卡隆 6SKT.

特性

外观:	棕色
分析:	pH 6.0-7.5
有效成份:	51-54%
电性:	阴离子
稳定性:	用于铬复鞣，中和浴。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

依丽卡隆 6SKT (2/3)



亚硫酸化加脂剂

绵羊鞋面				
回水	200%	水 25-30C		
	1%	雅化 CSAM	40' 或至软	排
复铬	100%	水 25-30C		
	0.2%	甲酸 (1:10)	15'	
	1%	黑染料	10'	
	5%	铬粉	40'	
	3%	依丽卡隆 6SKT		
	3%	聚合物 Polymer	30'	搅拌
	2%	甲酸钠	20'	pH 4.0-4.2
	过夜. 次日, 转 15'.			
				排
中和	150%	水 25-30C		
	2%	中和单宁	30'	
	2%	甲酸钠	10'	
	0.5%	小苏打	45'	pH 5.0-5.2
				排
洗	100%	水 35C	15'	排
复鞣	100%	水 35C		
	4%	树脂	20'	
	3%	复鞣剂 Dicyandiamide	20'	
	3%	聚合物 Polymer	20'	
	3%	依丽卡隆 6SKT	20'	
	4%	黑染料	40'	
	1%	刺云实栲胶 Tara		
	4%	坚木 Quebracho	30'	

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

依丽卡隆 6SKT (3/3)



亚硫酸化加脂剂

绵羊鞋面

	3%	填料 Filler		
	2%	分散单宁	20'	
加	100%	水 45-50C		
	4%	丽达隆 124		
	2%	丝卡隆 DSJ	45'	
	1.5%	甲酸 (1:10)	20'	
	1.5%	甲酸 (1:10)	20'	查 pH
				排
洗	100%	水 25-30C	15'	排
套染	200%	水 45-50C		
	1%	黑染料	10'	
	0.7%	阳离子油		
	0.05%	防酶剂	10'	
	0.8%	甲酸 (1:10)	10'	
	0.8%	甲酸 (1:10)	10'	排
洗	200%	水 25-30C	15'	排
堆积过夜. 次日, 正常运转				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".