

依丽卡隆 821 (1/3)



耐电解质亚硫酸化加脂剂

成份

依丽卡隆 821 是一种活性亚硫酸化加脂剂，耐光性和稳定性非常好。依丽卡隆 821 在浸酸浴能帮助打开皮面的皱纹，具有非常好的软度及舒适平滑的手感。

依丽卡隆 821 冷天不会产生任何油霜，即使长时间储存不会产生任何异味。为了达到最好的效果 依丽卡隆 821 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

- A. 各种皮革：浸酸浴：至 2.5% 依丽卡隆 821 裸皮重量。
- B. 各种蓝湿皮：铬复鞣浴：2-3% 依丽卡隆 821 消匀重量。
- C. 各种蓝湿皮：回水浴：至 2% 依丽卡隆 821。

特性

外观:	黄色液体
分析:	pH 5.0-6.5
有效成份:	58-61%
电性:	阴离子
稳定性:	用于浸酸，铬复鞣，复鞣浴。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

继续下页

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

依丽卡隆 821 (2/3)



耐电解质亚硫酸化加脂剂

服装革 鞋面革浸酸浴				
浸酸浴	50%	水 25-30C		
	10%	盐	10'	Be = 6-7
	1.5%	雅坦 MC	30'	
	1%	甲酸 (1:10)	20'	
	0.75%	雅坦 T (1:4)	30'	
	0.6%	硫酸 (1:10)	60'	pH 3.2-3.4
	0.5%	依丽卡隆 821	30'	
	0.5%	依丽卡隆 821	30'	
	0.5%	依丽卡隆 821	90'	
过夜, 专 20', 停 100'. 第二天按正常铬鞣工艺以后步骤进行。				

服装革, 家俱革及二层革铬复鞣浴				
回湿	200%	水 25-30C		
	3%	雅化 CSAM	40' 或至软	排水
洗水	100%	水 25-30C	10'	排水
铬复鞣	100%	水 25-30C		
	1%	依丽卡隆 821	20'	
	1%	依丽卡隆 821		
	1.5%	雅坦 MC	30'	
	4%	铬粉 (33% BCS)		
	3%	醋酸钠	120'	
过夜, 专 10', 停 110'. 第二天按正常工艺以后步骤进行。				

继续下页

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

依丽卡隆 821 (3/3)



耐电解质亚硫酸化加脂剂

鞋面革复鞣浴

回湿	100%	水 25-30C		
	3%	雅化 CSAM	40' 或至软	排水
洗水	100%	水 25-30C	10'	排水
铬复鞣	50- 100%	水 25-30C		
	1%	依丽卡隆 821		
	1.5%	雅坦 MC	30'	
	3-5%	铬粉 (33% BCS)		
	4%	醋酸钠	120'	
		按正常工艺以后步骤进行。		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".