

# 依丽卡隆 SFO (1/2)



海类型动物亚硫酸化加脂剂

## 成份

依丽卡隆 SFO 由海类型动物油组成，稳定性及柔软度优良。

依丽卡隆 SFO 皮革干燥后有非常少的鱼腥味。

依丽卡隆 SFO 产生手感很轻的皮。

依丽卡隆 SFO 冷天不会产生任何油霜，即使长时间储存不会产生任何异味。

为了达到最好的效果 依丽卡隆 SFO 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

## 应用范围

A. 服装革：至 8% 依丽卡隆 SFO.

B. 家俱革：6-8% 依丽卡隆 SFO.

C. 箱包革：4-6% 依丽卡隆 SFO.

## 特性

外观:	棕色液体
分析:	pH 6.0-7.5
有效成份:	53-55%
电性:	阴离子
稳定性:	用于主加脂浴。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

## 包装

120KGS 塑料桶

继续下页

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 依丽卡隆 SFO (2/2)



海类型动物亚硫酸化加脂剂

## 服装革，家俱革及二层革铬复鞣浴

回湿	200%	水 25-30C		
	3%	雅化 <b>CSAM</b>	40' 或至软	排水
洗水	100%	水 25-30C	10'	排水
铬复鞣	100%	水 25-30C		
	1%	依丽卡隆 <b>SFO</b>	20'	
	1%	依丽卡隆 <b>SFO</b>		
	1.5%	雅坦 <b>MC</b>	30'	
	4%	铬粉 (33% BCS)		
	3%	醋酸钠	120'	
过夜，专 10'，停 110'。第二天按正常工艺以后步骤进行。				

## 鞋面革复鞣浴

回湿	100%	水 25-30C		
	3%	雅化 <b>CSAM</b>	40' 或至软	排水
洗水	100%	水 25-30C	10'	排水
铬复鞣	50- 100%	水 25-30C		
	1%	依丽卡隆 <b>SFO</b>		
	1.5%	雅坦 <b>MC</b>	30'	
	3-5%	铬粉 (33% BCS)		
	4%	醋酸钠	120'	
按正常工艺以后步骤进行。				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".