

# 依丽卡隆 UWR (1/3)



耐高温，耐光加脂剂

## 成份

依丽卡隆 UWR 是专为产生白皮。

依丽卡隆 UWR 是一种亚硫酸化加脂剂，使皮具有软，重量轻及漂白性。

依丽卡隆 UWR 使皮具有优良柔软性，光滑，重量轻及漂白性。

依丽卡隆 UWR 冷天不会产生油霜，即使长时间储存也不会产生任何异味。

为了达到最好的效果 依丽卡隆 UWR 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

## 应用范围

A. 白色皮革：至 18%依丽卡隆 UWR。

## 特性

外观:	浅黄色黏稠状液体
分析:	pH 5.5-7.0
有效成份:	49-53%
电性:	阴离子
稳定性:	用于中和，复鞣，主加脂浴。对铬，铝鞣剂敏感。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

## 包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 依丽卡隆 UWR (2/3)



耐高温，耐光加脂剂

## 绵羊高尔夫手套

回水	200%	水 25-30C		
	0.8%	雅化 <b>CSAM</b>		
	0.3%	醋酸	30'	
				排
洗	100%	水 25-30C	10'	排
复铬	150%	水 25-30C		
	1.5%	雅坦 <b>T</b>	30'	
	4%	铬粉	60'	
	2%	甲酸钠	30'	排
洗	100%	水 25-30C	10'	排
中和	100%	水 25-30C		
	2%	醋酸钠	30'	
	0.5%	小苏打	30'	
	0.5%	小苏打	90'	
过夜. 次日, 转 15' pH = 5.0-5.5				
				排
洗	100%	水 25-30C	10'	排
复鞣	150%	水 25-30C		
	0.8%	雅丽丹 <b>White TNM</b>	15'	
	2%	依丽卡隆 <b>UWR</b>	30'	
加	100%	水 45-50C		
	3%	树脂		
	4%	依丽卡隆 <b>UWR</b>		
	4%	依丽卡隆 <b>6SKT</b>		
	1%	依丽卡隆 <b>50MD</b>		
	2%	丽达隆 <b>1908</b>		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

# 依丽卡隆 UWR (3/3)

耐高温，耐光加脂剂



## 绵羊高尔夫手套

	0.05%	防酶剂	90'	
	0.5%	甲酸 (1:10)	20'	
	1.0%	甲酸 (1:10)	20'	pH = 3.6
				排
洗	100%	水 25-30C	10'	排
套加脂	150%	水 45-50C		
	1%	丝卡隆 <b>S2733D</b>	15'	排
堆积过夜, 阴干. 正常运转.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".