

弗素 PNH



加脂剂

成份

弗素 PNH 适合产生软皮革，价格优惠。

弗素 PNH 由乳化剂，天然铀及卵磷脂组成。

弗素 PNH 可生产软及稍微松散纤维。

弗素 PNH 适合生产彩色皮革。

弗素 PNH 与弗素 S 不同，它不含蜡。

为了达到最好的效果 弗素 PNH 要预先加热到 25-35°C, 再把它乳化到 40-50°C 的水之中。

应用范围

A. 浅色二层贴膜家具革: 至 18% 弗素 PNH.

B. 浅色二层鞋面革: 至 16% 弗素 PNH.

C. 软二层鞋里革: 12-14% 弗素 PNH.

D. 手套革: 16-18% 弗素 PNH.

特性

外观:	棕色液体
分析:	pH 6.5-8.0
有效成份:	40-42%
电性:	阴离子
稳定性:	用于主加脂浴. 对铬, 铝敏感.
储存方法:	室温. 如出现霜冻, 搅拌均匀即可. 存放在阴凉及通风的库房.
保质期:	密封容器约 12 月.

包装

200KGS 铁桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".