

丽达隆 124 (1/3)



紧实鞋面硫酸化加脂剂

成份

丽达隆 124 是一种复合硫酸化加脂剂，适合生产紧实，丰满，弹性优良的皮革。

丽达隆 124 使皮具有干爽手感，同时拥有很好的油润性。

丽达隆 124 的渗透性中等，而不会产生空松结构。

丽达隆 124 可与其他阴离子加脂剂配合。

丽达隆 124 适合生产全粒面，轻磨面，毛孔压花鞋面革。

为了达到最好的效果 丽达隆 124 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 鞋面革：至 6% 丽达隆 124.

特性

外观:	黄色液体
分析:	pH 6.5-7.5
有效成份:	45-47%
电性:	阴离子
稳定性:	用于主加脂浴。对铬，铝敏感。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 124 (2/3)



紧实鞋面硫酸化加脂剂

牛鞋面				
回水	200%	水 25-30C		
	1%	雅化 CSAM		
	1%	雅化 325W	30'	排
洗	100%	水 25-30C	10'	排
复铬	200%	水 25-30C		
	0.5%	雅坦 T	30'	
	2%	铬粉	60'	
	2%	甲酸钠	30'	排
中和	150%	水 25-30C		
	1%	依丽卡隆 6SKT		
	2%	甲酸钠	15'	
	1%	依丽卡隆 6SKT		
	1.5%	中和单宁		
	0.5%	小苏打	30'	pH 4.5-4.7
				排
洗	100%	水 25-30C	10'	排
复鞣	50%	水 25-30C		
	4%	树脂	15'	
	3%	染料		
	2%	分散单宁		
	2%	栗木 Chestnut		
	3%	填料		
	3%	蛋白	60'	查 Ø
加	100%	水 45-50C		
	3%	丽达隆 124		
	3%	丝卡隆 DSJ		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 124 (3/3)

紧实鞋面硫酸化加脂剂



牛鞋面				
	0.05%	防酶剂	60'	
	0.75%	甲酸 (1:10)	20'	
	0.75%	甲酸 (1:10)	20'	排
洗	100%	水 25-30C	10'	排
套加脂	200%	水 25-30C		
	1%	阳离子油	20'	
	0.5%	甲酸 (1:10)	15'	排
搭马过夜. 次日, 伸展, 真空, 阴干.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".