

LEATHERNOL BT



亚硫酸化加脂剂本色皮革软皮油

成份

Leathernol BT 由天然亚硫酸化原材料组成.

Leathernol BT 适合产生本色皮革.

Leathernol BT 可在铬复鞣后, 不中和加入. 保护纤维不松散. 绒面短及紧实.

Leathernol BT 渗透性, 分散及吸收性优良.

为了达到最好的效果 **Leathernol BT** 要预先加热到 25-35°C, 再把它乳化到 40-50°C 的水之中.

应用范围

A. 衬里革: 8-10% Leathernol BT.

B. 二层革: 16-18% Leathernol BT.

C. 手套革: 12-14% Leathernol BT.

特性

外观:	黄色液体
分析:	pH 7.5-8.5
有效成分:	48-51%
电性:	阴离子
稳定性:	用于主加脂浴. 对铬, 铝鞣剂敏感.
储存方法:	室温. 如出现霜冻, 搅拌均匀即可. 存放在阴凉及通风的库房.
保质期:	密封容器约 18 月.

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".