

丽达隆 LP (1/3)



亚硫酸化加脂剂

成份

丽达隆 LP 是一种综合天然与合成油脂制成的亚硫酸化加脂剂。

丽达隆 LP 生产的皮重量很轻。

丽达隆 LP 使皮面具有柔软，丰满，滑爽及舒适感。

丽达隆 LP 冷天不会产生任何油霜。

为了达到最好的效果 丽达隆 LP 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 家具革：10-12% 丽达隆 LP.

B. 鞋面革：6-8% 丽达隆 LP.

C. 箱包革：8-10% 丽达隆 LP.

D. 衬里革：至 6% 丽达隆 LP.

特性

外观：棕色液体

分析：pH 6.0-7.5

电性：阴离子

稳定性：用于中和，复鞣，主加脂浴。对铬，铝鞣剂敏感。

储存方法：室温。如出现霜冻，搅拌均匀即可。

存放在阴凉及通风的库房。

保质期：密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 LP (2/3)



亚硫酸化加脂剂

山羊手套				
回水	200%	水 25-30C		
	1%	雅化 CSAM	15'	
	0.5%	小苏打	30'	pH 5.0-5.5
				排
染色	100%	水 25-30C		
	2%	分散单宁	15'	
	0.45%	黄色染料	60'	查 Ø
加	100%	水 45-50C		
	0.6%	甲酸 (1:10)	20'	pH 3.6-3.8
				排
中和	50%	水 25-30C		
	1%	依丽卡隆 821	10'	
	2%	雅坦 T	30'	
	2%	依丽卡隆 6SKT	30'	
	2%	依丽卡隆 6SKT	60'	
	3%	铝单宁 Aluminum Sulfate	30'	
	2%	醋酸钠	15'	
	0.5%	小苏打	15'	
	0.5%	小苏打	15'	
	0.5%	小苏打	15'	
	0.5%	小苏打	15'+90'	pH >5.5
		过夜. 次日, 转 15'.		
				排
洗	100%	水 25-30C	10'	排
加脂	150%	水 45-50C		
	4%	依丽卡隆 6SKT		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 LP (3/3)



亚硫酸化加脂剂

山羊手套

	4%	依丽卡隆 UWR		
	3	依丽卡隆 821		
	7.5%	丽达隆 LP		
	0.05	防酶剂	90'	
	0.5%	甲酸 (1:10)	10'	
	0.5%	甲酸 (1:10)	10'	
	0.5%	甲酸 (1:10)	20'	排
洗	100%	水 25-30C	10'	排
套加脂	200%	水 45-50C		
	1%	丝卡隆 S2733D	15'	排
堆积过夜. 阴干.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".