

丽达隆 NFS (1/4)



硫酸化加脂剂

成份

丽达隆 NFS 由硫酸化合成牛蹄油组成。

丽达隆 NFS 由稳定的原料制成，高温不会迁移，即使长时间储存不会产生任何异味。

丽达隆 NFS 的油润性很好，赋予皮革舒适的手感，紧实，柔软，有弹性。耐光性极佳。

为了达到最好的效果 丽达隆 NFS 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 小牛皮鞋面革：至 6-8% 丽达隆 NFS.

B. 软鞋面革：至 10% 丽达隆 NFS.

C. 植鞣革：4-6% 丽达隆 NFS.

特性

外观:	棕色液体
分析:	pH 6.0-7.6
有效成份:	58-62%
电性:	阴离子
稳定性:	用于复鞣，主加脂浴。对铬，铝鞣剂敏感。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 NFS (2/4)



硫酸化加脂剂

牛鞋面革

回水	200%	水 25-30C		
	1%	雅化 CSAM		
	2%	雅化 325W	30'	排
复铬	50%	水 25-30C		
	2%	雅坦 MCS	30'	
	5%	铬粉		
	1%	小苏打		
	2%	甲酸钠	60'	
加	200%	水 45-50C	120'	pH 3.8-4.2
				排
洗水	200%	水 25-30C	10'X2	排
复鞣	50%	水 25-30C		
	2%	中和单宁	15'	
	2%	醋酸钠		
	2%	分散单宁		
	2%	栗木 Chestnut		
	2%	荆树皮 Mimosa		
	2%	坚木 Quebracho		
	2%	染料		
	2%	填料		
	1%	树脂		
	3%	依丽卡隆 2012		
	3%	依丽卡隆 6SKT	60'	
	2%	分散单宁		
	2%	栗木 Chestnut		
	2%	荆树皮 Mimosa		

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 NFS (3/4)



硫酸化加脂剂

牛鞋面革

	2%	坚木 Quebracho		
	2%	染料 Dyestuff		
	2%	填料 Filler		
	1%	树脂 Acrylic		
	3%	依丽卡隆 2012		
	3%	依丽卡隆 6SKT	60'	
加	50%	水 25-30C		
	0.75%	甲酸 (1:10)	20'	
	0.75%	甲酸 (1:10)	20'	
	2%	铬粉	30'	
	O/N 转 20' 停 120'. 次日.			
加	200%	水 45-50C	60'	排
洗	200%	水 45-50C	10'X2	排
加脂	200%	水 45-50C		
	1.5%	染料	15'	
	1%	蛋白		
	1%	树脂		
	3%	丽达隆 NFS		
	2%	丽达隆 124		
	2%	优卡隆 L3C	40'	
	1%	蛋白		
	1%	树脂		
	3%	丽达隆 NFS		
	2%	丽达隆 124		
	2%	优卡隆 L3C		
	0.05%	防酶剂	60'	

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丽达隆 NFS (4/4)

硫酸化加脂剂



牛鞋面革

	0.75%	甲酸 (1:10)	20'	
	0.75%	甲酸 (1:10)	20'	排
洗	200%	水 45-50C	10'	排
搭马过夜, 伸展, 真空, 阴干.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".