

丽素隆 TSW



树脂加脂剂 | 无 APEO | 无 Cr 6+ | 无 PCP | 无 DMF

成份

丽素隆 TSW 由卵磷脂和高分子量聚合物组成。

丽素隆 TSW 赋予软，填充性，卵磷脂手感，皮面平坦而优良弹性。使粒面非常平滑而紧实。

丽素隆 TSW 在摔软后可避免松面。

丽素隆 TSW 冷天不会产生油霜，即使长时间储存也不会产生任何异味。

为了达到最好的效果 丽素隆 TSW 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 服装革：14-16% 丽素隆 TSW.

B. 家俱革：10-12% 丽素隆 TSW.

C. 软鞋面革：至 8% 丽素隆 TSW.

D. 箱包革：10-12% 丽素隆 TSW.

特性

外观:	黄棕色黏稠状液体
分析:	pH 6.0-7.0
有效成份:	49-52%
稳定性:	用于复鞣，中和，加脂浴。对铬，铝敏感。
电性:	阴离子
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".