

丝卡隆 DSJ (1/3)



硅油加脂剂

成份

丝卡隆 DSJ 由硅油，合成软皮剂及乳化剂组成。

丝卡隆 DSJ 非常适合软面纳帕革及鞋面纳帕革。

丝卡隆 DSJ 使皮具有软，毛绒绒，重量轻及填充性不强的皮革。

丝卡隆 DSJ 产生粒面细及小粒面纹路的摔纹革。

为了达到最好的效果丝卡隆 DSJ 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 服装革：至 20% 丝卡隆 DSJ.

B. 软鞋面革：12-14% 丝卡隆 DSJ.

C. 箱包革：10-12% 丝卡隆 DSJ.

特性

外观:	黄色液体
分析:	pH 5.5-7.0
电性:	阴离子
稳定性:	用于中和，复鞣，主加脂。对铬，铝敏感。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丝卡隆 DSJ (2/3)



硅油加脂剂

服装革 | 绵羊蓝湿皮 | 削匀革重

厚度	0.6-0.7 mm.			
洗水	300%	水 25-30°C		
	0.7%	雅化 325W		
	1.0%	雅化 CSAM	30'	pH=3.2-3.5
				排水
复鞣	150%	水 25-30°C		
	4.0%	铬单宁		
	2.0%	依丽卡隆 50MD	30'	
	2.0%	甲酸钠	15'	
	3.0%	中和单宁	15'	
	4.0%	树脂		
	2.0%	丽达隆 NFS		
	2.0%	软丙烯酸	30'	
	1.5%	小苏打	60'	pH=5.8-6.2
				BCG Ø = 蓝
			排水	
洗水	300%	水 25-30 °C	10'	
				排水
染料	100%	水 25-30 °C		
	2.0%	Tamol M 分散单宁		
	3.0%	染料	60'	
	200%	水 45-50 °C	5'	
	0.5%	甲酸 85% (1:10)	10'	
	1.0%	甲酸 85% (1:10)	15'	pH=3.6-3.8
			排水	
洗水	300%	水 45-50 °C		排水

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丝卡隆 DSJ (3/3)



硅油加脂剂

服装革 | 蓝湿绵羊 | 削匀革重

加脂浴	150%	水 45-50°C		
	5.0%	丝卡隆 DSJ		
	5.0%	优卡隆 L5TC	60'	
	1.0%	甲酸 85% (1:10)	30'	pH=3.2-3.4
				排水
表染	200%	水 45-50°C		
	1.0%	染料	20'	
	0.5%	甲酸 85% (1:10)	20'	pH=3.2-3.3
				排水
洗水	300%	水 25-30 °C	10'	
				排水
搭马 24h, 伸展, 阴干, 做软, 摔软.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".