

丝卡隆 SR (1/2)



阳离子表面硅油

成份

丝卡隆 SR 是一种反应性阳离子含硅加脂剂。

丝卡隆 SR 与皮革纤维的结合性特别强，赋予皮粒面及绒面舒适温暖的手感。

丝卡隆 SR 使皮具有微防水性，不影响涂饰工段。

由于丝卡隆 SR 的阳离子性，丝卡隆 SR 会与其它阴离子性化工如合成鞣剂，栲胶以及加脂剂反应。建议在单一溶液中使用 丝卡隆 SR。

使用过程中完全后，不水洗，直接排水及搭马过夜

应用范围

A. 顶加脂浴：至 2% 丝卡隆 SR。

B. 喷涂：溶解 1:4 丝卡隆 SR：水。喷两次

特性

外观：	乳白色液体
分析：	pH 4.0-5.0
有效成份：	32-35%
电荷：	阳离子
密度：	1.00-1.10 KG/L
稳定性：	对阴离子化料敏感。在单一溶液中使用。
储存条件：	在 5-30C 温度放置。对霜冻敏感。存放在阴凉及通风的库房。
保质期：	交付日期起，密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

丝卡隆 SR (2/2)



阳离子表面硅油

软箱包革

回水	200%	水 25-30C		
	2%	雅化 CSAM	30'	
	2%	雅化 325W	90'	至软
排水, 洗水	200%	水 25-30C	10'X3	
复鞣	100%	水 25-30C		
	2%	雅坦 T	60'	
	4%	依丽卡隆 66		
	2.8%	小苏打	120'	检查 pH
排水, 洗水	200%	水 25-30C	10'	
染色, 加脂	80%	水 25-30C		
	X%	染料	60'	至透心
	100%	水 45-50C		
	3%	优卡隆 L3C		
	3%	丝卡隆 DSJ	20'	混合好
	3%	优卡隆 L3C		
	3%	丝卡隆 DSJ	60'	混合好
	0.5%	甲酸 (1:10)	20'	
	1%	甲酸 (1:10)	20'	
排水, 洗水	100%	水 25-30C	10'	
顶层加脂	150%	水 25-30C		
	1%	丝卡隆 SR	15'	
	1%	丝卡隆 SR	15'	
排水	搭马过夜。按正常工艺以后步骤进行。不用水洗或伸展			

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".