

丝卡隆 XMN



硅油加脂剂

成份

丝卡隆 XMN 由磺酸酯, 硅油及乳化剂组成.

丝卡隆 XMN 非常适合软面纳帕包革及软鞋面纳帕革.

丝卡隆 XMN 适合产生白色皮.

丝卡隆 XMN 使皮具有软, 绵, 填充性好, 重量轻及弹性的皮革.

丝卡隆 XMN 产生粒面细及小粒面纹路的摔纹革.

为了达到最好的效果 丝卡隆 XMN 要预先加热到 25-35°C, 再把它乳化到 40-50°C 的水之中.

应用范围

A. 服装革: 至 20% 丝卡隆 XMN.

B. 软鞋面革: 12-14% 丝卡隆 XMN.

C. 箱包革: 10-12% 丝卡隆 XMN.

特性

| | |
|-------|------------------------------------|
| 外观: | 黄色液体 |
| 分析: | pH 6.0-7.0 |
| 有效成分: | 39-43% |
| 电性: | 阴离子 |
| 稳定性: | 用于中和, 复鞣, 主加脂. 对铬, 铝敏感. |
| 储存方法: | 室温. 如出现霜冻, 搅拌均匀即可. 存放在阴凉及通风的库房. |
| 保质期: | 密封容器约 12 月. |

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".