

# 优卡隆 GL



复合加脂剂

## 成份

优卡隆 GL 是复合加脂剂，由天然油脂，卵磷脂及合成柔软剂组成，适合产生软皮革。

优卡隆 GL 渗透性中等，使皮具有干爽及丝绸手感。

优卡隆 GL 产生的皮革软及重量轻。

优卡隆 GL 适合产生鲜艳至深颜色水染革，染料吸收均匀。

优卡隆 GL 可大量使用，不会糊面及粘粘表面手感。

优卡隆 GL 的耐光性优良。

为了达到最好的效果，优卡隆 GL 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

## 应用范围

- A. 羊服装革: 至 16% 优卡隆 GL。
- B. 水牛家具革: 至 14% 优卡隆 GL。
- C. 黄牛家具革: 至 12% 优卡隆 GL。
- D. 平纹小牛鞋面革: 至 5% 优卡隆 GL。

## 特性

|       |                                  |
|-------|----------------------------------|
| 外观:   | 黄色液体                             |
| 分析:   | pH 6.5-8.0                       |
| 电性:   | 阴离子                              |
| 稳定性:  | 用于中和，复鞣，主加脂浴。对铬，铝敏感。             |
| 储存方法: | 室温。如出现霜冻，搅拌均匀即可。<br>存放在阴凉及通风的库房。 |
| 保质期:  | 密封容器约 12 月。                      |

## 包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".