

优卡隆 L3C (1/4)



复合卵磷脂加脂剂

成份

优卡隆 L3C 是一种卵磷脂加脂剂，具有优良分散性及乳化性。

优卡隆 L3C 产生的皮赋予柔软及平滑粒面。

优卡隆 L3C 对绒面具有短毛及丝绸效应。

优卡隆 L3C 可分散动物天然脂肪，帮助防止油霜现象。

优卡隆 L3C 耐光性优良。

为了达到最好的效果，优卡隆 L3C 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 服装革：至 12% 优卡隆 L3C.

B. 软鞋面纳帕革：至 8% 优卡隆 L3C.

C. 二层鞋面革：至 6% 优卡隆 L3C.

D. 箱包革：6-8%优卡隆 L3C.

特性

外观:	黄色液体
分析:	pH 5.5-7.0
电性:	阴离子
稳定性:	用于中和，复鞣，主加脂浴。对铬，铝敏感。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 L3C (2/4)



复合卵磷脂加脂剂

仿鹿				
回水	200%	水 25-30C		
	2%	雅化 CSAM	10'	
	2%	雅化 325W	30'	排
复铬	50%	水 25-30C		
	2%	雅坦 MCS	15'	
	1%	染料	10'	
	0.5%	依丽卡隆 50MD		
	5%	铬粉		
	0.7%	小苏打	90'	
加	150%	水 45-50C	30'	pH 4.0-4.4
				排
中和	200%	水 25-30C		
	2%	雅坦 T	20'	
	3%	依丽卡隆 6SKT	20'	
	1%	NA 113	30'	
	3%	依丽卡隆 6SKT		
	1.5%	NA 113	90'	排
洗	100%	水 25-30C	10'	排
复鞣, 加脂	100%	水 25-30C		
	2%	丝卡隆 1102		
	2%	丝卡隆 DSJ		
	2%	优卡隆 L3C	20'	
	1%	白单宁	20'	
	2%	丝卡隆 1102		
	2%	丝卡隆 DSJ		
	2%	优卡隆 L3C	20'	

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 L3C (3/4)



复合卵磷脂加脂剂

仿鹿				
	0.75%	甲酸 (1:10)	20'	
	1.5%	丝卡隆 1102		
	1.5%	丝卡隆 DSJ		
	1.5%	优卡隆 L3C		
	0.05	防酶剂	40'	
	1%	白单宁		
	0.75%	甲酸 (1:10)	20'	pH 3.8-4.2
				排
洗	100%	水 25-30C	10'	排
套加脂	200%	水 25-30C		
	1%	丝卡隆 S2733D	15'	
	1%	丝卡隆 S2733D	15'	
搭马过夜. 阴干. 无机械操作.				
干重量				
回水	600%	水 25-30C		
	1%	雅化 325W	20'	排
渗透染	100%	水 25-30C		
	2%	分散单宁	10'	
	2%	染料	90'	至透心
	300%	水 45-50C		
	1%	甲酸 (1:10)	15'	排
套染 1	300%	水 45-50C		
	0.7%	染料	15'	
	1%	甲酸 (1:10)	15'	排

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 L3C (4/4)



复合卵磷脂加脂剂

仿鹿				
套染 2	300%	水 45-50C		
	0.7%	染料	15'	
	1%	甲酸 (1:10)	15'	
	1%	甲酸 (1:10)	15'	排
套加脂	200%	水 45-50C		
	2%	丝卡隆 1102		
	2%	丝卡隆 DSJ		
	2%	优卡隆 L3C	20'	
	1%	甲酸 (1:10)	15'	排
洗	200%	水 25-30C	10'	排
搭马过夜, 伸展, 阴干, 绷板. 摔软 6 小时.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".