

优卡隆 L5TC (1/3)



卵磷脂加脂剂

成份

优卡隆 L5TC 是一种综合卵磷脂加脂剂与天然乳化剂。

优卡隆 L5TC 用于生产软，蓬松，光滑，紧实，轻及舒适手感的皮革。

优卡隆 L5TC 具有优良填充作用，使皮革丰满手感。

优卡隆 L5TC 对染色浴没有任何影响。

优卡隆 L5TC 大量使用不会糊面。

为了达到最好的效果，优卡隆 L5TC 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 羊软面革：至 10% 优卡隆 L5TC。

B. 家俱革：8-10% 优卡隆 L5TC。

C. 箱包革：6-8% 优卡隆 L5TC。

特性

外观:	黄色液体
分析:	pH 5.5-7.0
有效成份:	48-52%
电性:	阴离子
稳定性:	用于中和，复鞣，主加脂浴。对铬，铝敏感。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 L5TC (2/3)



卵磷脂加脂剂

手套 | 蓝湿绵羊 | 削匀革重

厚度	0.7-0.8 mm.			
洗水	300%	水 25-30°C		
	0.7%	雅化 325W		
	1.0%	雅化 CSAM	30'	pH=3.2-3.5
				排水
复鞣	150%	水 25-30°C		
	4.0%	软单宁		
	2.0%	依丽卡隆 50MD	30'	
	3.0%	中和单宁	15'	pH=4.8-5.0
	3.0%	软单宁		
	2.0%	优卡隆 L5TC		
	3.0%	软单宁	30'	
	1.5%	小苏打	60'	pH=5.6-5.8
				BCG Ø = 蓝
洗水	300%	水 25-30°C	15'	
				排水
染料	100%	水 25-30°C		
	4.0%	软单宁	10'	
	0.5%	染料渗透助剂		
	1.0%	染料	60'	
	200%	水 45-50°C	5'	
	0.5%	甲酸 85% (1:10)	20'	
	0.5%	甲酸 85% (1:10)	20'	pH=3.9
				排水
洗水	300%	水 45-50°C	10'	
				排水

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 L5TC (3/3)

卵磷脂加脂剂



手套 蓝湿绵羊 削匀革重				
加脂浴	150%	水 45-50°C		
	6.0%	丽达隆 LP		
	6.0%	优卡隆 L5TC		
	1.5%	甲酸 85% (1:10)	30'	pH=3.5
				排水
洗水	300%	水 20-25°C	10'	
				排水
搭马 24h, 伸展, 阴干, 做软, 摔软.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".