

优卡隆 N7YC (1/3)



汽车用革 | 低雾化值

成份

优卡隆 N7YC 由低雾化值原料组成。

优卡隆 N7YC 使皮具有优良柔软度及低气味。

优卡隆 N7YC 压花能力优良。

优卡隆 N7YC 适合其他软面革，例如纳帕及服装革。

为了达到最好的效果 优卡隆 N7YC 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

A. 汽车用革：至 12% 优卡隆 N7YC.

B. 纳帕革：4-6%优卡隆 N7YC.

C. 箱包革：6-8%优卡隆 N7YC.

特性

外观:	黄色液体
分析:	pH 5.8-7.2
有效成份:	45-48%
稳定性:	用于中和，复鞣，主加脂浴。对铬，铝敏感。
电性:	阴离子
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 N7YC (2/3)

汽车用革 | 低雾化值



汽车坐垫 | 公牛蓝湿皮 | 削匀革重

厚度	1.2-1.3 mm.			
洗水	200%	水 25-30°C		
	0.5%	雅化 DDA		
	0.7%	雅化 CSAM	40'	pH=3.4
				排
洗水	200%	水 25-30°C	10'	
				排水
中和	150%	水 25-30°C		
	0.1%	甲酸 85% (1:10)	5'	
	3.0%	铬粉		
	2.0%	铬单宁	60'	
	1.0%	染料	20'	
	2.5%	甲酸钠	40'	pH=4.4
	1.0%	软丙烯酸		
	2.0%	优卡隆 N7YC	20'	
	0.6%	小苏打	60'	pH=5.1
				排
复鞣	60%	水 25-30°C		
	2.0%	丙烯酸低雾化	30'	
	3.0%	优卡隆 N7YC	15'	
	0.5%	染色助剂	10'	
	3.5%	染料	60'	
	2.5%	中和单宁		
	5.0%	替代型单宁		
	5.0%	双氰胺		
	7.0%	刺云实栲胶	90'	

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".

优卡隆 N7YC (3/3)

汽车用革 | 低雾化值



汽车坐垫 | 公牛蓝湿皮 | 削匀革重

	60%	水 45-50°C		
	10%	优卡隆 N7YC	50'	
	0.7%	甲酸 85% (1:10)	20'	
	1.0%	甲酸 85% (1:10)	20'	
	1.0%	甲酸 85% (1:10)	30'	pH=3.3
				排水
洗水	150%	水 25-30°C	15'	
				排水
固定	150%	水 25-30°C		
	0.5%	固色剂	15'	
				排水
搭马 24h, 伸展, 湿绷板干燥, 喷水回湿, 做软.				

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".