

优卡隆 TS-20 (1/3)



紧实鞋面加脂剂

成份

优卡隆 TS-20 由天然及合成柔软剂组成。

优卡隆 TS-20 产生丰满及紧实鞋面革。

优卡隆 TS-20 的耐光性优良，对高温不容易变黄。

优卡隆 TS-20 对涂层的粘着性没有影响。

用 优卡隆 TS-20 加工的皮革有舒适的气味，特别是与植物栲胶和合成鞣剂混合应用。

为了达到最好的效果 优卡隆 TS-20 要预先加热到 25-35C，再把它乳化到 40-50C 的水之中。

应用范围

- A. 紧实鞋面：至 4% 优卡隆 TS-20.
- B. 软鞋面：至 6% 优卡隆 TS-20.
- C. 二层鞋面：至 6% 优卡隆 TS-20.
- D. 摔纹箱包革：至 8% 优卡隆 TS-20.

特性

外观:	棕色液体
分析:	pH 6.0-7.5
有效成份:	53-57%
电性:	阴离子
稳定性:	用于铬复鞣，中和浴。对铬，铝中等稳定性。
储存方法:	室温。如出现霜冻，搅拌均匀即可。 存放在阴凉及通风的库房。
保质期:	密封容器约 12 月。

包装

120KGS 塑料桶

The information and technical advice are provided to you 'as is' and the Company expressly disclaims all warranties of any kind, either implied or expressed. You agree to indemnify and hold harmless the Company and its representatives, subsidiaries, affiliates, related parties, officers, directors, employees, agents from any claim or demand, including reasonable legal fees, that may be filed by any third party, arising out of your conduct or connection with the use of "Product Literature" or "Technical Information" or "Technical Advice" or "Technical Guidance" or any "Recommendation".